

ALLURE

QUALITY

CONSTRUCTION		Tufted Cut Pile
MACHINE GAUGE		1/10 th Gauge
PILE HEIGHT	ISO 1766	13,5 mm
TUFT DENSITY	ISO 1763	201.500 tuft/sqm
PILE WEIGHT		1.700 gms/sqm
TOTAL CARPET WEIGHT	ISO 8543	2.700 gms/sqm
CARPET THICKNESS	ISO 1765	16,5 mm
WIDTH		2 & 4 meters (5 on request)
ROLL SIZE		Maximum 25m

COMPOSITION

PILE CONTENT	ISO 1833	100% Luxury Ultra Soft SD Fibers
SECONDARY BACKING		Syntetic Jute

PERFORMANCE

SUITABILITY		Extra heavy domestic
WIRA ABRASION TEST	PD 6527	Exceed 50.000 rubs
STATIC LOADING	ISO 3416	20,5% Thickness loss after 24 hours
DYNAMIC LOADING	ISO 2094	28,8% Thickness loss after 1,000 impacts
TUFT ANCHORAGE	ISO 4919	Above 1,0 Kg

COLOUR FASTNESS

LIGHT FASTNESS	ISO 105-B02	Above Grade 6 on all colours
WET FASTNESS	ISO 105:E01	Above Grade 4/5 on all colours
SHAMPOO FASTNESS	BS 1006:UK-TB	Above Grade 4/5 on all colours

THERMAL VALUE

TOG VALUE	ISO 5085-1	1,8 tog
-----------	------------	---------

FLAMMABILITY

METHENAMINE PILL TEST	ISO 6925	Pass
-----------------------	----------	------

CHEMICAL IMPACT

FORMALDEHYDE	CE	E1
--------------	----	----

BIOLOGICAL ATTACK

MOTH/INSECT RESISTANT		Insect and rot proof
-----------------------	--	----------------------

USE CLASSIFICATION

