











## SAFARI - Dati tecnici

	<p><b>CONSTRUCTION</b></p> <p>MACHINE GAUGE 5/32nd Loop Pile          PILE HEIGHT 5 mm          TUFT DENSITY 89,279 loops/m<sup>2</sup>          PILE WEIGHT 1,017 gms/m<sup>2</sup>          30 oz/yd<sup>2</sup>          TOTAL CARPET WEIGHT 1,954 gms/m<sup>2</sup>          CARPET THICKNESS 7.9 mm          WIDTH 4 &amp; 5 metre</p>
	<p><b>COMPOSITION</b></p> <p>PILE CONTENT 100% Wool          PRIMARY BACKING Woven Polypropylene          SECONDARY BACKING Woven Secondary</p>
 <p>EHD</p>  <p>MC</p>	<p><b>PERFORMANCE</b></p> <p>SUITABILITY Extra Heavy Domestic / Medium Contract          WIRA ABRASION TEST PD 6527:Clause 17 Exceeds 13,200 Rubs          STATIC LOADING ISO 3416 28.6% Thickness loss after 24 hrs recovery          DYNAMIC LOADING ISO 2094 26.5% Thickness loss after 1,000 impacts          TUFT ANCHORAGE ISO 4919 Above 1kg</p>
	<p><b>COLOUR FASTNESS</b></p> <p>LIGHT FASTNESS ISO 105-B02 5/6 on all colours          WET FASTNESS ISO 105-E01 4/5 on all colours          SHAMPOO FASTNESS BS 1006:UK-TB 4/5 on all colours</p>
	<p><b>THERMAL VALUE</b></p> <p>TOG VALUE 1.2 Tog          THERMAL RESISTANCE ISO 5085-1 0.12 m<sup>2</sup> k/w</p>
	<p><b>FLAMMABILITY</b> CE</p> <p>CE MARK RATING Cfl, S1          HOT METAL NUT TEST BS4790 Pass - Low radius of ignition          METHENAMINE PILL TEST ISO 6925 Pass</p>
	<p><b>CHEMICAL IMPACT</b> CE</p> <p>FORMALDEHYDE E1          REACH CERTIFICATE Compliant</p>
	<p><b>BIOLOGICAL ATTACK</b></p> <p>MOTH / INSECT RESISTANT Eulan Treated</p>
	<p>ANTI STATIC -0.3 kv (Requirement less than +2.0 kv)</p>

### GENERAL INFORMATION

**Installation** - In all contract locations an 'all over' stick down method is recommended to BS 5325 (1983). If underlay is required the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

**Maintenance** - Please note all pile carpets of any fibre type will flatten to some extent in traffic lanes although regular vacuuming will help to allay this. This 'flattening' is a normal reaction to localised traffic in both domestic and contract locations and is not a manufacturing fault, therefore will not be accepted as the basis for any claim. Rubber soled shoes when used constantly in heavy traffic areas can sometimes act abrasively on the surface of the carpet therefore it is recommended that their use is limited. Loop pile carpets should be vacuumed with a cylinder cleaner or suction head only. Occasionally wool may contain traces of the sheep's natural environment. These traces can be easily removed and do not affect the durability of the carpet. Joins in loop pile carpet can sometimes be visible, especially so in patterned loop pile. The use of seaming cement is advisable.

**Heather Shades** - In manufacturing heather shades several contrasting colours are blended to create a 'heather' yarn. As such random coloured flecks will be apparent in the carpet. These flecks form part of the effect and are not considered the basis for any claim.

**Matching** - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 4 & 5 metre widths cannot be guaranteed.

**Important** - A good quality underlay is always recommended when fitting a new carpet. Minimum order length 1.5 metres.