

TECHNICAL INFORMATION

TOUCH


TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	construction	ISO 2424	1/10" soft cut pile
poolmateriaal	yarn content	ISO 2424	polyamide PA 6
rug	backing	ISO 2424	Ceneva® Starback
gebruiksklasse	suitability	EN 1307	23/33 heavy contract use
poolgewicht	pile weight	ISO 2424	1900 gr/m ²
totaal gewicht	total weight	ISO 8543	2850 gr/m ²
pooldikte	pile height	ISO 1766	9.4 mm
totaal dikte	total thickness	ISO 1765	12.0 mm
noppental	tuft density	ISO 1763	267000 tufts/m ²
breedte	width	CEN/TS 14159	ca 4 and 5 m
rapport	pattern repeat	CEN/TS 14159	0 mm
warmteoorlaatweerstand	thermal resistance	ISO 8302	0.19 m ² K/W
brandklasse	flammability	ISO 13501-1	Cfl-s1
contactgeluidsisolatie	impact sound insulation	ISO 140-8/717-2	25 dB
structure	struttura	ISO 2424	1/10" soft cut pile
composition	composizione	ISO 2424	polyamide PA 6
dossier	sottofondo	ISO 2424	Ceneva® Starback
classement d'usage	classe utilizzo	EN 1307	23/33 heavy contract use
poids de velours	peso felpa	ISO 2424	1900 gr/m ²
poids total	peso totale	ISO 8543	2850 gr/m ²
hauteur du velours	spessore felpa	ISO 1766	9.4 mm
épaisseur totale	spessore totale	ISO 1765	12.0 mm
densité	densità felpa	ISO 1763	267000 tufts/m ²
dimensions	altezza	CEN/TS 14159	ca 4 and 5 m
raccord	rapporto disegno	CEN/TS 14159	0 mm
résistance thermique	resistenza termica	ISO 8302	0.19 m ² K/W
comportement au feu	classe reazione al fuoco	ISO 13501-1	Cfl-s1
isolation acoustique	isolamento acustico	ISO 140-8/717-2	25 dB

COLOURS

102 Glacier	169 Weasel
122 Calm	184 Loam
133 Mole	189 Graphite
136 Heaven	
149 Nimbus	

PRODIS RATING AND INFORMATION



EN 14041
EN 1307



PRODIS: B8F732FE
DOP: 1025-124990

CONTACT INFORMATION



Super Tuft Moquettes S.r.l.
Via Valsesia, 84
28061 Biandrate (NO) - Italy
Tel. 0321 838552
E-mail: info@supertuft.it
www.supertuft.it
P.IVA 01001670031